



# Highland International, Inc.

## Technical Data Sheet



### 26 Series "Fast Dry" Non-Sanding Rust Inhibitive Primer/Sealer

**26 Series** is a high solids, multi-purpose coating designed to seal previously primed surfaces or, due to its superior rust inhibitive properties, be applied directly to metal as a prime coat. Specifically designed for use at OEMs, its exceptional leveling properties and fast dry times make it an excellent choice for sealing previously primed surfaces. It may be topcoated with a variety of products including urethanes, epoxies, acrylics, and alkyls.

<b>Vehicle Type:</b>	Modified Phenolic Alkyd	<b>Dry-Time:</b>	<b>Normal Application</b>	<b>Hot Application</b>
<b>Pigmentation:</b>	Zinc Phosphate (Lead & Chromate Free)	<b>To Touch</b>	30 min.	N/A
<b>Reducers for:</b>	Not Normally Required	<b>Tack Free</b>	1 hour	N/A
<b>If Desired:</b>	#64 Reducer	<b>To Topcoat</b>	30 min. - 1 hour	N/A
<b>Mixing Ratio:</b>	Single Package	<b>To Handle</b>	2 hours	N/A
<b>Pot Life:</b>	N/A	<b>V.O.C.:</b>	3.5 lbs. per gallon (419 grams/liter)	
<b>Volume Solids:</b>	50%	<b>Shelf Life:</b>	1 Year Minimum	
<b>Theoretical Coverage:</b>	800 Sq. Ft. per gallon @ 1 mil DFT	<b>Finish:</b>	Flat	
<b>Flash Point:</b>	45°F (Lowest Flashing Component)	<b>Color:</b>	Off-White or Selected Range	
<b>Recommended DFT:</b>	2-3 mils	<b>Weight:</b>	11.5-13.5 lbs. per gal. (varies with color)	

**Preparation:** Minimum surface preparation should be in accordance with SSPC-SP6 Commercial Blast cleaning. When blast cleaning is not an option, SSPC-SP3 Powertool or SSPC-SP2 Wire Brushing is acceptable and provides good results. Also, water jetting in accordance with SSPC-SP12 is acceptable. Etch aluminum or galvanized surfaces prior to priming. All surfaces to be painted should be dry and free of all foreign contaminants.

**Application Requirements:** (1) Stir thoroughly prior to use. (2) Apply at a rate of 267 to 400 square feet per gallon to obtain the recommended film thickness. (3) Topcoat with Highland #36 Series, #37 Series, #64 Series, #150 Series or #65C Series.

**Method of Application:**

**Conventional Spray**

**Airless Spray:**

<b>Gun:</b>	DeVilbiss MBC-510	<b>Gun:</b>	Graco 205-591
<b>Fluid Tip:</b>	E	<b>Pump:</b>	30:1
<b>Air Cap:</b>	704	<b>Tip Range:</b>	3.011 - 4.015 @ 1800 psi min.
<b>Atomizing Pressure:</b>	60 psi	<b>Hose:</b>	3/8 inch ID
<b>Pot Pressure:</b>	15-20 psi		
<b>Hose:</b>	3/8 inch ID		
<b>Brush or Roller:</b>	Brush may be used for touch-up		
<b>Clean Up:</b>	Clean all equipment with lacquer thinner, MEK, or acetone		

**Safety Precautions:** (a) Use normal precautions such as gloves, facemasks, and barrier creams. (b) Adequate ventilation must be maintained. In confined areas, workmen must wear constant flow airline respirators. (c) If product comes into contact with skin, wash thoroughly with lukewarm water or diluted Boric Acid, and obtain immediate medical attention. (d) This product contains **FLAMMABLE** materials. Keep away from sparks and open flames. Observe **NO SMOKING** regulations. (e) All electrical equipment and installations should conform to NEC regulations. In areas where explosion hazards exist, workmen should be required to use non-ferrous tools, and to wear conductive, non sparking shoes. (f) Observe low flash regulations. (g) Refer to Material Safety Data Sheet (MSDS) for complete safety instructions.

The technical data listed herein has been compiled for your convenience and guidelines and is based upon our experience and knowledge. However, since we have no control over the use of this information or this product, no warranty express or implied is intended or given. Highland assumes no responsibility whatsoever for coverage, performance or any other damage, including injuries from use of this information of products recommended herein. However, when applied according to manufacturers specifications, these products will perform as indicated.

**P. O. Box 3564 Boone, NC 28607**  
**800-444-1438**  
**www.highland-international.com**