

Highland International, Inc.

Technical Data Sheet

485C Series Dry-Fall High Performance 2-K Epoxy Direct to Metal Coating High Solids High Build Surface Tolerant

485C Series is a High Performance 2-Component epoxy DTM designed for overspray to dry to a powder within 10-20 feet from point of application allowing painting to continue without the worry of paint overspray damage to nearby vehicles or equipment. 485C Series may be applied over tightly bonded rust or mil scale and offers outstanding chemical, water, weathering, and corrosion protection. If desired, the Dry-Fall effect may be eliminated or controlled with the proper reducer selection.

Vehicle Type:	Polyamine Epoxy	Dry-Time:	Normal Application	Hot Application
Pigmentation:	Varies with color (Zinc Phosphate)	To Recoat	10-15 Min. (Max 28 Days)	N/A
Reducers for		Tack Free	30 Minutes	N/A
Dry-Fall Application:	30-E for 80°F and above	Dry Hard	2-3 Hours	N/A
	32-E for 80°F and below	Complete Cure	5-7 Days @ 77°F	N/A
Mixing Ratio:	9:1 Base to Activator	Put in Service	24 Hours	N/A
Pot Life:	3 Hours @ 77°F	V.O.C.:	3.2 Lbs. per Gal. (400 Grams/Liter)	
Volume Solids:	50% (+/- 1%)	Shelf Life:	1 Year Minimum	
Theoretical Coverage:	800 Sq. Ft. per gallon @ 1 mil DFT	Finish:	Satin	
Flash Point:	-4°F Lowest Flashing Component	Color:	Selected Range	
Recommended DFT:	A) 4-6 mils for very good corrosion protection in moderate conditions			
	B) 6-10 mils for maximum corrosion protection even in severe chemical & atmospheric conditions			
Recommended WFT:	for A) 10-15.5 mils wet after reduction will achieve 4-6 mils DFT			
	for B) 15.5-25.5 mils wet after reduction will achieve 6-10 mils DFT			

Preparation: To assure Dry-Fall effect, do not apply in temperatures below 45°F or on surfaces below 40°F. In applications where surface temperatures are above 150°F, consult a Highland International representative. For immersion, a SSPC-SP5 White Metal Blast is required. Commercial Blast, SSPC-SP6 is recommended for steel surfaces when practical. Where blast cleaning is not practical, SSPC-SP3 Powertool or Wire Brushing is acceptable and provides excellent results. All surfaces should be dry and free of contaminants.

Mix 1/2 Gallon Part "A" Activator with 4.5 Gallons Part "B" Base. **Allow minimum 20 minute induction period BEFORE reduction**
For Dry-Fall effect in 20+ feet, you **must** reduce activated material 10% or for Dry-Fall effect within 10-20 feet you **must** reduce activated material 10-20%. Reduce with one of the following Highland Exempt Reducers:
#30-E Highland VOC Exempt Warm Weather Dry-Fall Reducer for temperatures 80°F and above
#32-E Highland VOC Exempt Cold Weather Dry-Fall Reducer for temperatures below 80°F

Electric Airless spray equipment is not recommended. We have found this equipment does not generate proper atomization required for Highland Dry-Fall Products

Method of Application:	Conventional Spray	Airless Spray:	
Gun:	DeVilbiss MBC-510	Gun:	Graco 205-591
Fluid Tip:	E	Pump:	30:1
Air Cap:	704	Tip Range:	3.011-3.013 to 4.011-4.015 @ 1800 psi
Atomizing Pressure:	60 psi	Hose:	3/8 inch ID (Do not use whip lines)
Pot Pressure & Hose:	15-20 psi 3/8" ID		
Brush or Roller:	Both are acceptable	Clean Up:	Use 30-E or 32-E Reducer or lacquer thinner.

Safety Precautions: (a) Use normal precautions such as gloves, facemasks, and barrier creams. (b) Adequate ventilation must be maintained. In confined areas, workmen must wear constant flow airline respirators. (c) If product comes into contact with skin, wash thoroughly with lukewarm water or diluted Boric Acid, and obtain immediate medical attention. (d) This product contains **FLAMMABLE** materials. Keep away from sparks and open flames. Observe **NO SMOKING** regulations. (e) All electrical equipment and installations should conform to NEC regulations. In areas where explosion hazards exist, workmen should be required to use non-ferrous tools, and to wear conductive, non sparking shoes. (f) Observe low flash regulations. (g) Refer to Material Safety Data Sheet (MSDS) for complete safety instructions.

The technical data listed herein has been compiled for your convenience and guidelines and is based upon our experience and knowledge. However, since we have no control over the use of this information or this product, no warranty express or implied is intended or given. Highland assumes no responsibility whatsoever for coverage, performance or any other damage, including injuries from use of this information of products recommended herein. However, when applied according to manufacturers specifications, these products will perform as indicated.